

BN

658967

P/00/001  
Section 29

AUSTRALIA  
Patents Act 1990

**PATENT REQUEST : STANDARD PATENT**

I/We, being the person(s) identified below as the Applicant(s), request the grant of a Standard Patent to the person(s) identified below as the Nominated Person(s), for an invention described in the accompanying complete specification.

**Applicant(s) and  
Nominated Person(s):** TIOXIDE SPECIALTIES LIMITED

**Address:** TIOXIDE HOUSE  
137-143 HAMMERSMITH ROAD  
LONDON W14 OQL  
ENGLAND

**Invention Title:** OIL-IN-WATER EMULSIONS

**Name(s) of Actual  
Inventor(s):** GERD HERBERT DAHMS

**Address for Service:** GRIFFITH HACK & CO  
509 ST KILDA ROAD  
MELBOURNE VIC 3004

**Attorney Code:** HA


**BASIC CONVENTION APPLICATION DETAILS**

<b>Application No:</b>	<b>Country:</b>	<b>Application Date:</b>
9204387.6	GB	29 February 1992

**DATED:** 28 January 1993

**TIOXIDE SPECIALTIES LIMITED**

**GRIFFITH HACK & CO**



Patent Attorney for and  
on behalf of the Applicant

AUSTRALIA  
Patents Act 1990

**NOTICE OF ENTITLEMENT**

I/We TIOXIDE SPECIALTIES LIMITED

of TIOXIDE HOUSE  
137-143 HAMMERSMITH ROAD  
LONDON W14 0QL  
ENGLAND

being the applicant(s) in respect of an application for a patent for an invention entitled OIL-IN-WATER EMULSIONS, state the following:

1. The nominated person(s) has/have, for the following reasons, gained entitlement from the actual inventor(s):

THE NOMINATED PERSON IS THE ASSIGNEE OF THE INVENTOR.

2. The nominated person(s) has/have, for the following reasons, gained entitlement from the basic applicant(s) listed on the patent request:

THE APPLICANT AND NOMINATED PERSON IS THE BASIC APPLICANT.

3. The basic application(s) listed on the request form is/are the first application(s) made in a Convention country in respect of the invention.

DATE: 28 January 1993

TIOXIDE SPECIALTIES LIMITED

**GRIFFITH HACK & CO**



Patent Attorney for and  
on behalf of the applicant(s)



AU9332055

(12) PATENT ABRIDGMENT (11) Document No. AU-B-32055/93  
(19) AUSTRALIAN PATENT OFFICE (10) Acceptance No. 658967

(54) Title  
OIL-IN-WATER EMULSIONS

International Patent Classification(s)  
(51)<sup>5</sup> A61K 007/40 A61K 007/46

(21) Application No. : 32055/93

(22) Application Date : 28.01.93

(30) Priority Data

(31) Number	(32) Date	(33) Country
9204387	29.02.92	GB UNITED KINGDOM

(43) Publication Date : 02.09.93

(44) Publication Date of Accepted Application : 04.05.95

(71) Applicant(s)  
TIOXIDE SPECIALTIES LIMITED

(72) Inventor(s)  
GERD HERBERT DAHMS

(74) Attorney or Agent  
GRIFFITH HACK & CO , GPO Box 1285K, MELBOURNE VIC 3001

(57) Claim

1. An oil-in-water emulsion comprising from 0.5 per cent to 30 per cent by weight with respect to the total weight of emulsion of particles of a metallic oxide having an average primary particle size of less than 0.2 micron, said emulsion containing an emulsifier system comprising one or more emulsifiers, said emulsifier system being present in an amount of less than 10 per cent by weight with respect to the total weight of emulsion and said emulsifier system having a hydrophile-lipophile balance less than 6, from 5 per cent to 30 per cent by weight with respect to the total weight of emulsion of an oil phase and at least 60 per cent by weight with respect to total weight of emulsion of an aqueous phase.

21 A process for preparing an oil-in-water emulsion comprising mixing an aqueous dispersion of particles of a metallic oxide having an average primary particle size of less than 0.2 micron with one or more emulsifiers and an oil phase to form an oil-in-water emulsion wherein the total amount of emulsifiers present

**(11) AU-B-32055/93**  
**(10) 658967**

**-2-**

in the oil-in-water emulsion so formed is less than 10 per cent by weight, the particles of metallic oxide comprise from 0.5 per cent to 30 per cent by weight of the emulsion, the oil phase comprises 5 per cent to 30 per cent by weight of the emulsion and an aqueous phase comprises at least 60 per cent by weight of the emulsion.

658967

AUSTRALIA  
Patents Act 1990

**COMPLETE SPECIFICATION**  
**STANDARD PATENT**

**Applicant(s):**

**TIOXIDE SPECIALTIES LIMITED**

**Invention Title:**

**OIL-IN-WATER EMULSIONS**

Th following statement is a full description of this  
invention, including the best method of performing it known  
to me/us:

OIL-IN-WATER EMULSIONS

This invention relates to oil-in-water emulsions and especially to oil-in-water emulsions containing metallic oxides having a small particle size.

Oil-in-water emulsions containing metallic oxides with a small particle size are known in which the total amount of all emulsifiers present is, typically, 18 to 20 percent by weight of the emulsion. Furthermore, it is normally necessary to ensure a balance between hydrophobic and hydrophilic emulsifiers and the particular balance depends upon the nature of the oil phase of the emulsion.

Typical hydrophilic emulsifiers are ethoxylated compounds which generally utilise relatively complex production methods and which are not easily biodegradable.

It is an object of this invention to provide stable oil-in-water emulsions which overcome some of the disadvantages of known oil-in-water emulsions.

According to the present invention there is provided an oil-in-water emulsion comprising from 0.5 percent to 30 percent by weight with respect to the total weight of emulsion of particles of a metallic oxide having an average primary particle size of less than 0.2 micron, said emulsion containing an emulsifier system comprising one or more emulsifiers, said emulsifier system being present in an amount of less than 10 percent by weight with respect to the total weight of emulsion and said emulsifier system having a hydrophile-lipophile balance less than 6, from 5 percent to 30 percent by weight with respect to the total weight of emulsion of an oil phase and at least 60 percent by weight with respect to total weight of emulsion of an aqueous phase.

Also according to the invention a process for preparing an oil-in-water emulsion comprises mixing an aqueous dispersion of particles of a metallic oxide having an average primary particle size of less than 0.2 micron with one or more emulsifiers and an oil phase under conditions  
5 in which an oil-in-water emulsion is formed wherein the total amount of emulsifiers present in the oil-in-water emulsion so formed is less than 10 per cent by weight, the particles of metallic oxide comprise from 0.5 per cent to 30 per cent by weight of the emulsion, the oil phase comprises 5 per cent to 30 per cent by weight of the emulsion and an aqueous phase  
10 comprises at least 60 per cent by weight of the emulsion.

In preferred embodiments of the product and the process of the invention the metallic oxide comprises an oxide of titanium, zinc or iron.

The average primary particle size of the particles of metallic oxide used to prepare the oil-in-water emulsion of the invention is less  
15 than 0.2 micron and where the particles are substantially spherical then this size will be taken to represent the diameter. However, the invention also encompasses particles of metallic oxides which are non-spherical and in such cases the average primary particle size refers to the largest dimension.

20 Preferably the average primary particle size of the particles is from 0.01 to 0.15 micron and more preferably from 0.01 to 0.06 micron when they are substantially spherical. Particularly useful products can be prepared using substantially spherical particles having an average primary particle size in the range 0.01 to 0.03 micron. For particles  
25 having an acicular shape the average largest dimension of the primary

particles is preferably less than 0.15 micron and more preferably from 0.02 to 0.10 micron.

When the metallic oxide is titanium dioxide the particles are preferably acicular in shape and have a ratio of largest dimension to shortest dimension of from 8:1 to 2:1.

When the metallic oxide is zinc oxide the particles preferably have an average primary particle size of 0.005 to 0.15 micron and more preferably have an average primary particle size of 0.03 to 0.07 micron.

The particles of metallic oxide may comprise substantially pure metallic oxide but may also carry an inorganic coating or organic coating. For example, particles of titanium dioxide can be coated with oxides of other elements such as oxides of aluminium, zirconium or silicon and a form of acicular, coated titanium dioxide which is especially useful in the products of this invention is disclosed in UK Patent GB 2 205 088.

The particles of metallic oxides may also carry, if desired, a coating of one or more organic materials such as polyols, amines, alkanolamines, polymeric organic silicon compounds, hydrophilic polymers such as polyacrylamide, polyacrylic acid, carboxymethyl cellulose and xanthan gum or surfactants.

The emulsions of the current invention contain a relatively small amount of one or more emulsifiers by comparison with previously known emulsions. Preferably the total amount of emulsifiers present in the emulsion is less than 5% by weight. Also the quantity of hydrophilic emulsifiers present is preferably less than 10% by weight of the total



quantity of emulsifiers present and, in the most preferred case, no hydrophilic emulsifiers are present.

Generally, the hydrophile-lipophile balance (HLB value) of the emulsifier system is less than 6 and, preferably, the HLB value is less than 5. This contrasts with the belief generally held heretofore that an emulsifier suitable for forming an oil-in-water emulsion should have a higher HLB value (e.g. 8 to 18).

When hydrophilic emulsifiers are present then suitable emulsifiers include polyoxyethylene derivatives of sorbitan fatty acid esters, polyoxyethylene fatty acid esters, polyoxyethylene fatty ethers, phosphate esters, fatty alcohol sulphates, polyglycoside ethers, polyglycoside esters and alkali metal salts of sulphosuccinate esters.

Hydrophobic emulsifiers suitable for use in the products of the invention include lipid emulsifiers such as fatty alcohols, fatty acids, glyceryl esters, sorbitan esters, methylglycoside esters and sucrose esters. Generally, in contrast to hydrophilic emulsifiers these emulsifiers are easy to produce from renewable raw materials, are readily biodegradable and do not contain toxic side products.

In carrying out the process of the invention an aqueous dispersion of a metallic oxide having a primary particle size as hereinbefore defined is used. Typically, the dispersion is prepared by milling the metallic oxide in water in the presence of a particulate grinding medium and in the presence of a dispersing agent.

UK Patent Application GB 2 226 018 discloses an aqueous dispersion of titanium dioxide having an acicular shape containing a

dispersing agent which is a polycarboxylic acid or a salt thereof. The dispersions described in GB 2 226 018 are particularly suitable for use in the method of the current invention when it is desired to produce an oil-in-water emulsion containing titanium dioxide.

5       The technique described in GB 2 226 018 can be used to prepare aqueous dispersions of metallic oxides other than titanium dioxide which are suitable for use in the method of the invention.

      Suitable dispersing agents which can be used to prepare dispersions of metallic oxides according to GB 2 226 018 include  
10 polyacrylic acids, substituted acrylic acid polymers, acrylic copolymers, sodium and/or ammonium salts of polyacrylic acids and sodium and/or ammonium salts of acrylic copolymers.

      The total quantity of emulsifiers used is less than 10% by weight of the emulsion and suitable emulsifiers are as hereinbefore described.

15       The composition of the oil phase is chosen to suit the proposed use for the emulsion. For example, when the emulsion is intended for use as a sunscreen the oil phase will generally comprise paraffin oils, triglyceride esters, esters of fatty acids and fatty alcohols or silicone oils.

      The aqueous dispersions of metallic oxide, emulsifier and oil  
20 phase are mixed under conditions which produce an oil-in-water emulsion.

      In a typical process, the aqueous dispersion is mixed, if required, with other water miscible ingredients to form an aqueous phase and this phase and the oil phase are separately heated to at least 40°C, preferably  
25 to at least 60°C and more preferably to at least 70°C. These two phases

are then mixed under vigorous stirring in the presence of the emulsifier or emulsifiers. Mixing equipment which has found use for preparing cosmetic creams, lotions etc. is suitable for preparing the emulsions. High shear mixers/homogenisers are particularly suitable.

5           The emulsifier(s) are usually added to the aqueous phase before the oil phase is mixed with the aqueous phase.

Other ingredients can be added to the emulsion depending upon the intended use. These ingredients may be introduced in any convenient manner. For example they can be mixed with the emulsion  
10 or added to the aqueous dispersion or the oil phase before these components are mixed together. As examples, perfumes, antioxidants, moisturisers, thickeners and preservatives are normally added to emulsions which are intended for use as cosmetics.

The oil-in-water emulsions of this invention find use as  
15 sunscreens, as skin protectants, as moisturisers and as after-sun lotions and are particularly useful in preparing products which are transparent to visible light but absorbent to UV light. The emulsions can also be used in, for example, hair conditioners, hair sprays and pharmaceutical ointments.

20           The emulsions use smaller quantities of emulsifiers than known emulsions and the emulsifiers which are preferred are easily produced and readily bio-degradable.

The process of the invention enables emulsions with the above desirable properties to be produced and in which the selection of

emulsifier(s) is less dependent upon the nature of the oil phase than hitherto.

Emulsions prepared according to the invention have been shown to possess better Sun Protection Factors (SPF values) than emulsions containing similar quantities of metallic oxide but prepared by previously known methods.

The invention is illustrated by the following examples.

### **EXAMPLE 1**

		<b><u>Parts by weight</u></b>
10	1) Sorbitan Monostearate (sold under the trade name Span 60)	4.00
	2) Stearyl alcohol	2.50
	3) Paraffin oil	10.00
	4) Dispersion of titanium dioxide in water	12.50
15	(sold under the trade name Tioveil AQ)	
	5) Glycerol	4.00
	6) Carbomer 934	0.08
	7) Demineralised water	to 100

Ingredients 1 to 3 were mixed together and heated to 80°C to form an oil component. Ingredients 4 to 7 were mixed together and also heated to 80°C to form an aqueous component. The oil component was added to the aqueous component with intensive stirring (motor-driven paddle stirrer). The resulting emulsion was homogenised for two minutes using a high-shear mixer/homogeniser (Silverson), and then allowed to cool to room temperature with slow agitation. The resulting emulsion was stable for greater than two months at room temperature.

**EXAMPLE 2**

An suncream comprising an oil-in-water emulsion was prepared using the following formulation.

	<b><u>Phase A</u></b>	<b><u>% by weight</u></b>
5	Isopropyl Myristate	4.00
	Mineral Oil	6.50
	Grape Seed Oil	2.50
	Stearyl Alcohol	2.00
	Petrolatum	2.00
10	<b><u>Phase B</u></b>	
	Sorbitan Stearate (Span 60 <sup>[1]</sup> )	6.00
	Disodium Ricinoleamido MEA-Sulfosuccinate (Rewoderm S 1333 <sup>[2]</sup> )	0.20
	Titanium Dioxide Aqueous Dispersion (Tioveil AQ <sup>[3]</sup> )	15.00
15	Glycerin	4.00
	Allantoin	0.20
	D-Panthenol <sup>[4]</sup>	0.80
	Demineralised Water	56.40
	<b><u>Phase C</u></b>	
20	5-Chloro-2-methyl-4-isothiazolin-3-one (and)	
	2-methyl-4-isothiazolin-3-one (Kathon CG <sup>[5]</sup> )	0.20
	Crematest S Timbuktu Perfume <sup>[6]</sup>	0.20

**Suppliers**

[1] ICI Specialty Chemicals, [2] REWO, [3] Tioxide Specialties Limited,

25 [4] Hoffmann La Roche, [5] Rohm & Haas, [6] Dragoco.

Phase A (oil phase) and Phase B (aqueous phase) were separately heated to 80°C. Phase A was added to Phase B under intensive stirring (motor driven paddle stirrer). The resultant mixture was then homogenised by mixing for 1 minute in a domestic kitchen stirrer (Braun model 4169) and the homogenised mixture was allowed to cool with gentle agitation. Phase C was added to this mixture when the temperature reached 35°C and agitation was stopped when the temperature fell to 25°C.

### 10 **EXAMPLE 3**

A suncream comprising an oil-in-water emulsion was prepared using the following formulation.

#### **Phase A** **% by weight**

	Isohexadecane (Arlamol HD <sup>[1]</sup> )	6.00
15	Octyl Stearate (Cetiol 868 <sup>[6]</sup> )	4.00
	Decyl Oleate (Cetiol V <sup>[6]</sup> )	2.00
	Behenyl Alcohol	1.00
	dl- $\alpha$ -Tocopheryl Acetate <sup>[4]</sup>	1.00

#### **Phase B**

20	Sorbitan Stearate (Span 60 <sup>[1]</sup> )	6.00
	Disodium Ricinoleamido MEA-Sulfosuccinate (Rewoderm S 1333 <sup>[2]</sup> )	0.20
	Titanium Dioxide Aqueous Dispersion (Tioveil AQ <sup>[3]</sup> )	10.00
	Allantoin	0.20

D-Panthenol <sup>[4]</sup>	0.80
Demineralised Water	68.78

**Phase C**

5	5-Chloro-2-methyl-4-isothiazolin-3-one (and) 2-methyl-4-isothiazolin-3-one (Kathon CG <sup>[5]</sup> )	0.02
---	---	------

**Suppliers**

[1] ICI Specialty Chemicals, [2] REWO, [3] Tioxide Specialties Limited,  
[4] Hoffmann La Roche, [5] Rohm & Haas, [6] Henkel

10 The ingredients were mixed using the method described in  
Example 2.

**EXAMPLE 4**

A suncream comprising an oil-in-water emulsion was prepared  
using the following formulation.

15	<b><u>Phase A</u></b>	<b><u>% by weight</u></b>
	Isopropyl Myristate	3.00
	Mineral Oil	6.00
	Grape Seed Oil	2.00
	Stearyl Alcohol	2.00
20	dl- $\alpha$ -Tocopheryl Acetate <sup>[4]</sup>	1.00

**Phase B**

	Sorbitan Stearate (Span 60 <sup>[1]</sup> )	6.00
	Disodium Ricinoleamido MEA- Sulfosuccinate (Rewoderm S 1333 <sup>[2]</sup> )	0.20
25	Tioxide Dioxide Aqueous Dispersion (Tioveil AQ <sup>[3]</sup> )	5.00

Glycerin	4.00
Allantoin	0.20
D-Panthenol <sup>[4]</sup>	0.80
Demineralised Water	69.40

5 **Phase C**

5-Chloro-2-methyl-4-isothiazolin-3-one (and)	
2-methyl-4-isothiazolin-3-one (Kathon CG <sup>[5]</sup> )	0.20
Crematest S Timbuku Perfume <sup>[6]</sup>	0.20

**Suppliers**

- 10 [1] ICI Specialty Chemicals, [2] REWO, [3] Tioxide Specialties Limited,  
[4] Hoffmann La Roche, [5] Rohm & Haas, [6] Dragoco

The ingredients were mixed using the method described in Example 2.

15 **EXAMPLE 5**

A suncream comprising an oil-in-water emulsion was prepared using the following formulation.

<b><u>Phase A</u></b>	<b><u>% by weight</u></b>
Isopropyl Myristate	4.00
20 Mineral Oil	6.50
Grape Seed Oil	2.50
Stearyl Alcohol	2.00
Petrolatum	2.00



**Phase B**

	Sorbitan Stearate (Span 60 <sup>[1]</sup> )	5.00
	Titanium Dioxide Aqueous Dispersion (Tioveil AQ <sup>[3]</sup> )	10.00
	Glycerin	4.00
5	Allantoin	0.20
	D-Panthenol <sup>[4]</sup>	0.80
	Demineralised Water	62.60

**Phase C**

	5-Chloro-2-methyl-4-isothiazolin-3-one (and)	
10	2-methyl-4-isothiazolin-3-one (Kathon CG <sup>[5]</sup> )	0.20
	Crematest S Timbaktu Perfumel <sup>[6]</sup>	0.20

**Suppliers**

[1] ICI Specialty Chemicals, [2] REWO, [3] Tioxide Specialties Limited,  
[4] Hoffmann La Roche, [5] Rohm & Haas, [6] Dragoco

15        The ingredients were mixed using the method described in  
Example 2.

**EXAMPLE 6**

20        A sunlotion comprising an oil-in-water emulsion was prepared  
using the following formulation.

**Phase A**

		<b><u>% by weight</u></b>
	Caprylic/Capric Triglyceride (Miglyol 812N <sup>[6]</sup> )	4.00
	Mineral Oil	6.00
	Grape Seed Oil	2.00
25	Petrolatum	2.00

Stearyl Alcohol	0.50
dl- $\alpha$ -Tocopheryl Acetate <sup>[4]</sup>	2.00

**Phase B**

	Sorbitan Stearate (Span 60 <sup>[1]</sup> )	3.00
5	Disodium Ricinoleamido MEA-Sulfosuccinate (Rewoderm S 1333 <sup>[2]</sup> )	0.20
	Titanium Dioxide Aqueous Dispersion (Tioveil AQ <sup>[3]</sup> )	10.00
	Glycerin	4.00
	Allantoin	0.20
10	D-Panthenol <sup>[4]</sup>	0.80
	Demineralised Water	65.28

**Phase C**

5-Chloro-2-methyl-4-isothiazolin-3-one (and)	
2-methyl-4-isothiazolin-3-one (Kathon CG <sup>[5]</sup> )	0.02

**15 Suppliers**

[1] ICI Specialty Chemicals, [2] REWO, [3] Tioxide Specialties Limited,  
[4] Hoffmann La Roche, [5] Rohm & Haas, [6] Huls

The ingredients were mixed using the method described in  
Example 2.

20

**EXAMPLE 7**

A sunlotion comprising an oil-in-water emulsion was prepared  
using the following formulation.

25

	<b><u>Phase A</u></b>	<b><u>% by weight</u></b>
--	-----------------------	---------------------------

	Isohexadecane (Arlamol HD <sup>[1]</sup> )	6.00
	Octyl Stearate (Cetiol 868 <sup>[6]</sup> )	4.00
	Decyl Oleate (Cetiol V <sup>[6]</sup> )	2.00
5	dl- $\alpha$ -Tocopheryl Acetate <sup>[4]</sup>	1.00

	<b><u>Phase B</u></b>	
--	-----------------------	--

	Sorbitan Stearate (Span 60 <sup>[1]</sup> )	4.00
	Disodium Ricinoleamido MEA-	
	Sulfosuccinate (Rewoderm S 1333 <sup>[2]</sup> )	0.20
10	Titanium Dioxide Aqueous Dispersion (Tioveil AQ <sup>[3]</sup> )	10.00
	Allantoin	0.20
	D-Panthenol <sup>[4]</sup>	0.80
	Demineralised Water	71.78

	<b><u>Phase C</u></b>	
--	-----------------------	--

15	5-Chloro-2-methyl-4-isothiazolin-3-one (and)	
	2-methyl-4-isothiazolin-3-one (Kathon CG <sup>[5]</sup> )	0.02

	<b><u>Suppliers</u></b>	
--	-------------------------	--

[1] ICI Specialty Chemicals, [2] REWO, [3] Tioxide Specialties Limited,  
[4] Hoffmann La Roche, [5] Rohm & Haas, [6] Henkel.

20        The ingredients were mixed using the method described in  
Example 2.

	<b><u>EXAMPLE 8</u></b>	
--	-------------------------	--

25        A sunlotion comprising an oil-in-water emulsion was prepared  
using the following formulation.

**Phase A****% by weight**

	Caprylic/Capric Triglyceride (Miglycol 812N <sup>[6]</sup> )	4.00
	Mineral Oil	6.00
	Grape Seed Oil	2.00
5	Petrolatum	2.00
	dl- $\alpha$ -Tocopheryl Acetate <sup>[4]</sup>	2.00

**Phase B**

	Sorbitan Stearate (Span 60 <sup>[1]</sup> )	3.00
	Disodium Ricinoleamido MEA-	
10	Sulfosuccinate (Rewoderm S 1333 <sup>[2]</sup> )	0.20
	Titanium Dioxide Aqueous Dispersion (Tioveil AQ <sup>[3]</sup> )	10.00
	Glycerin	4.00
	Allantoin	0.20
	D-Panthenol <sup>[4]</sup>	0.80
15	Demineralised Water	65.78

**Phase C**

	5-Chloro-2-methyl-4-isothiazolin-3-one (and)	
	2-methyl-4-isothiazolin-3-one (Kathon CG <sup>[5]</sup> )	0.02

**Suppliers**

- 20 [1] ICI Specialty Chemicals, [2] REWO, [3] Tioxide Specialties Limited,  
[4] Hoffmann La Roche, [5] Rohm & Haas, [6] Huls.

The ingredients were mixed using the method described in Example 2.

**EXAMPLE 2**

A sunlotion comprising an oil-in-water emulsion was prepared using the following formulation.

<b><u>Phase A</u></b>		<b><u>% by weight</u></b>
5	Caprylic/Capric Triglyceride (Miglycol 812N <sup>[6]</sup> )	4.00
	Mineral Oil	6.00
	Grape Seed Oil	2.00
	Petrolatum	2.00
	Isoamyl p-Methoxycinnamate	
10	(Neo Heliopan Type E 1000 <sup>[7]</sup> )	3.00
	dl- $\alpha$ -Tocopheryl Acetate <sup>[4]</sup>	2.00
<b><u>Phase B</u></b>		
	Sorbitan Stearate (Span 60 <sup>[1]</sup> )	3.00
	Disodium Ricinoleamido MEA-	
15	Sulfosuccinate (Rewoderm S 1333 <sup>[2]</sup> )	0.20
	Titanium Dioxide Aqueous Dispersion (Tioveil AQ <sup>[3]</sup> )	10.00
	Glycerin	4.00
	Allantoin	0.20
	D-Panthenol <sup>[4]</sup>	0.80
20	Demineralised Water	62.78
<b><u>Phase C</u></b>		
	5-Chloro-2-methyl-4-isothiazolin-3-one (and)	
	2-methyl-4-isothiazolin-3-one (Kathon CG <sup>[5]</sup> )	0.02

**Suppliers**

[1] ICI Specialty Chemicals, [2] REWO, [3] Tioxide Specialties Limited, [4] Hoffmann La Roche, [5] Rohm & Haas, [6] Huls, [7] Haarmann & Reimer.

5

The ingredients were mixed using the method described in Example 2.

10

15

20

25

**THE CLAIMS DEFINING THE INVENTION ARE AS FOLLOWS:**

1. An oil-in-water emulsion comprising from 0.5 per cent to 30 per cent by weight with respect to the total weight of emulsion of particles of a metallic oxide having an average primary particle size of less than 0.2 micron, said  
5 emulsion containing an emulsifier system comprising one or more emulsifiers, said emulsifier system being present in an amount of less than 10 per cent by weight with respect to the total weight of emulsion and said emulsifier system having a hydrophile-lipophile balance less than 6, from 5 per cent to 30 per cent  
10 by weight with respect to the total weight of emulsion of an oil phase and at least 60 per cent by weight with respect to total weight of emulsion of an aqueous phase.
2. An oil-in-water emulsion according to claim 1 in which the metallic oxide is an oxide of titanium, zinc or iron.
- 15 3. An oil-in-water emulsion according to claim 1 or 2 in which the particles of metallic oxide are substantially spherical and have an average primary particle size of from 0.01 to 0.15 micron.
4. An oil-in-water emulsion according to claim 3 in which the average primary particle size is from 0.01 to 0.06 micron
- 20 5. An oil-in-water emulsion according to claim 4 in which the average primary particle size is from 0.01 to 0.03 micron

6. An oil-in-water emulsion according to claim 1 or 2 in which the particles of metallic oxide have an acicular shape and the average largest dimension of the primary particles is less than 0.15 micron.
- 5 7. An oil-in-water emulsion according to claim 6 in which the average largest dimension of the primary particles is from 0.02 to 0.10 micron.
8. An oil-in-water emulsion according to claim 6 in which the metallic oxide is titanium dioxide and the primary particles have a ratio of longest dimension to shortest dimension in the range of from 8:1 to 2:1.
- 10 9. An oil-in-water emulsion according to claim 1 or 2 in which the metallic oxide is zinc oxide having an average primary particle size of from 0.005 to 0.15 micron.
- 10 10. An oil-in-water emulsion according to claim 9 in which the average primary particle size is from 0.03 to 0.07 micron.
- 15 11. An oil-in-water emulsion according to any one of the preceding claims in which the particles of metallic oxide carry an inorganic or an organic coating
12. An oil-in-water emulsion according to claim 11 in which the metallic oxide is titanium dioxide and the particles have a coating of an oxide of aluminium, zirconium or silicon.
- 20 13. An oil-in-water emulsion according to claim 11 or 12 in which the particles of metallic oxide carry a coating of a polyol, an amine, an alkanolamine, a polymeric silicon compound, polyacrylamide, polyacrylic acid, carboxymethyl cellulose, xanthan gum or a surfactant.



14. An oil-in-water emulsion according to any one of the preceding claims in which the total amount of emulsifiers present in the emulsion is less than 5 per cent by weight with respect to weight of emulsion.

5 15. An oil-in-water emulsion according to any one of the preceding claims in which less than 10 per cent by weight of the total quantity of emulsifiers present comprises hydrophilic emulsifiers.

16. An oil-in-water emulsion according to any one of the preceding claims in which no hydrophilic emulsifiers are present.

10 17. An oil-in-water emulsion according to any preceding claim in which the hydrophile-lipophile balance is less than 5.

18. An oil-in-water emulsion according to any one of claims 1 to 15 in which at least one of the emulsifiers present is a polyoxyethylene derivative of a sorbitan fatty acid ester, a polyoxyethylene fatty acid ester, a polyoxyethylene fatty ether, a phosphate ester, a fatty alcohol sulphate, a polyglycoside ether, a  
15 polyglycoside ester or an alkali metal salt of a sulphosuccinate ester.

19. An oil-in-water emulsion according to any one of the preceding claims in which at least one of the emulsifiers present is a fatty alcohol, a fatty acid, a glyceryl ester, a sorbitan ester, a methylglycoside ester or a sucrose ester

20 20. An oil-in-water emulsion according to any one of the preceding claims in which the oil phase comprises a paraffin oil, a triglyceride ester, an ester of a fatty acid and a fatty alcohol or a silicone oil

21. A process for preparing an oil-in-water emulsion comprising mixing an aqueous dispersion of particles of a metallic oxide having an average primary particle size of less than 0.2 micron with one or more emulsifiers and an oil phase to form an oil-in-water emulsion wherein the total amount of emulsifiers present in the oil-in-water emulsion so formed is less than 10 per cent by weight, the particles of metallic oxide comprise from 0.5 per cent to 30 per cent by weight of the emulsion, the oil phase comprises 5 per cent to 30 per cent by weight of the emulsion and an aqueous phase comprises at least 60 per cent by weight of the emulsion.

22. A process according to claim 21 in which the aqueous dispersion of metallic oxide is prepared by milling the metallic oxide in water in the presence of a particulate grinding medium and in the presence of a dispersing agent.

23. A process according to claim 22 in which the dispersing agent is a polycarboxylic acid or a salt thereof.

24. A process according to claim 23 in which the polycarboxylic acid or salt thereof is a polyacrylic acid, a substituted acrylic acid polymer, an acrylic copolymer, a sodium or ammonium salt of a polyacrylic acid or a sodium or ammonium salt of an acrylic copolymer.

25. A process according to claims 23 or 24 in which the particles of metallic oxide are acicular particles of titanium dioxide.

26. A process according to any one of claims 21 to 25 in which an aqueous phase comprising the aqueous dispersion and an oil phase are separately heated to a temperature of at least 40°C and mixed in the presence of one or more emulsifiers with vigorous stirring.

27. A process according to claim 26 in which the aqueous phase and the oil phase are separately heated to at least 60°C.

28. A process according to claim 27 in which the aqueous phase and the oil phase are separately heated to at least 70°C.

29. A sunscreen, moisturiser or after-sun lotion comprising an oil-in-water emulsion according to any one of claims 1 to 20.

30. A method of preparing an oil-in-water emulsion substantially as hereinbefore described with reference to the Examples

31. An oil-in-water emulsion substantially as herein described with reference to the Examples.

32. A sunscreen, moisturiser or after-sun lotion substantially as herein described with reference to the Examples.

DATED THIS 20TH DAY OF FEBRUARY 1995

**TIOXIDE SPECIALTIES LIMITED**

By Its Patent Attorneys:

**GRIFFITH HACK & CO.,**

Fellows Institute of Patent  
Attorneys of Australia

**ABSTRACT OF THE DISCLOSURE**

**OIL-IN-WATER EMULSIONS**

An oil-in-water emulsion containing 0.5% to 30% metallic oxides having a particle size of less than 0.2 micron, less than 10% total emulsifier, 5% to 30% of an oil phase and at least 60% of an aqueous phase is provided.

The invention also makes available a method of preparing such emulsions in which the emulsion is formed by use of a dispersion in water of the metallic oxide particles.

By comparison with previously known emulsions of this type relatively small quantities of emulsifiers are used and it is possible to use an emulsion system with a low HLB value (e.g. less than 6). Preferably no hydrophilic emulsifiers are used.

The emulsions are suitable for preparing UV-absorbing compositions such as sunscreens, moisturisers and after-sun lotions. The ability to use no, or little, hydrophilic emulsifiers is advantageous since, in, general, these emulsifiers are not biodegradable whereas hydrophobic emulsifiers generally are biodegradable.